



WOOD LEGNO

special adhesive for wood

Line

POLYESTER

Function

SPECIAL DUAL-COMPONENT HIGH SEAL ADHESIVE FOR AFFIXING AND SURFACING WOOD

Materials

WOOD

How to use

For best results, mix 2% to 3% of the catalyst (dibenzoyl peroxide) with the adhesive concentrate. The catalyst paste formula is easier to measure accurately. A consistent mixture will facilitate uniform catalysis. The speed of catalysis is effected by temperature and by the quantity of catalyst. An excess of hardener will increase the catalysis rate, but weakens the adhesive's seal. Surfaces to be treated must be clean and dry; porosity and unevenness of the surface favor the best adhesion (varnished surfaces must be sanded before application).

Packaging

500-750ml

Characteristics

FOR MORE INFORMATIONS ASKING TECHNICAL DATA SHEET. □

Important

A PRELIMINARY TEST IN A SMALL, HIDDEN, AREA IS RECOMMENDED BEFORE THE APPLICATION.